AMENDMENT NO. 3 MARCH 2021

TO

IS 2222 : 1991 SPECIFICATION FOR BURNT CLAY PERFORATED BUILDING BRICKS

(Fourth Revision)

(*Page* 1, *clause* **3.1**) — Substitute 'IS 2248' *for* 'IS 2248 : 1991'.

(*Page* 1, *clause* **6.1**) — Substitute the following for the existing:

'**6.1** The area of perforation shall be between 20 percent and 36 percent of total area of the corresponding face of the brick.'

(*Page* 1, *clause* **7.1**) — Substitute 'IS 3495 (Part 1)' *for* 'IS 3495 (Parts 1 to 4) : 1991'.

(*Page* 1, *clause* **7.2**) — Substitute 'IS 3495 (Part 2)' *for* 'IS 3495 (Parts 1 to 4) : 1991'.

(*Page* 1, *clause* **7.3**) — Substitute 'IS 3495 (Part 3)' *for* 'IS 3495 (Parts 1 to 4) : 1991'.

(*Page* 1, *clause* **7.4**) — Substitute 'IS 3495 (Part 4)' *for* 'IS 3495 (Parts 1 to 4) : 1991'.

(*Page* 2, Annex A, *see also Amendment No* 2) — Substitute the following for the existing entries:

'*IS No.*	*Title*
2248 : 1992	Glossary of terms relating to clay products for building (*second revision*)

IS No.	*Title*
3495	Methods of tests of burnt clay building bricks
(Part 1) : 2019	Determination of compressive strength (*fourth revision*)
(Part 2) : 2019	Determination of water absorption (*fourth revision*)
(Part 3) : 2019	Determination of efflorescence (*fourth revision*)
(Part 4) : 2019	Determination of warpage (*fourth revision*)
5454 : 1978	Methods for sampling of clay building bricks (*first revision*)'

(CED 30)

Publication Unit, BIS, New Delhi, India